

SELECTION & SPECIFICATION DATA

Type	Two Part Epoxy Resin
Description	<p>Novocoat HF1200 Epoxy is a versatile two-component epoxy resin used as a primer or as a binder for polymer toppings such as slurry, broadcast or trowel-applied flooring, concrete resurfacing/leveling underlayment, and high friction surface (HFS) pavement overlays. (Aggregate not included.)</p> <p>Among its many uses, Novocoat HF1200 Epoxy binds broadcast aggregate, selected by the Department of Transportation to enhance surface friction or delineate color, to the underlying concrete or asphalt pavement at intersections, entrance/exit ramps, crosswalks, school crossings, bridge surfaces, grades, curves, roundabouts, toll plazas, bike paths, and more.</p>
Features	<ul style="list-style-type: none"> • 100% solids, no VOCs • Self-priming • Versatile resin binder • Low stress, highly flexible film
Uses	<p>Universal binder for:</p> <ul style="list-style-type: none"> • Slurry, broadcast and trowel-applied flooring • Concrete resurfacing/leveling underlayment • High friction surface (HFS) pavement overlays
Color	Clear
Finish	Gloss
Primer	Self-priming. May be applied over most types of coatings.
Topcoats	Acrylics, Epoxies, Polyurethanes, Broadcast
Dry Film Thickness	40 – 60 mils per coat
Solids Content	99 – 100% by volume
Maximum Dry Temperature Resistance	<p>Continuous: 176°F (80°C)</p> <p>Non-Continuous: 203°F (90°C)</p>
Limitations	Will lose gloss, discolor, and chalk in sunlight exposure.

SUBSTRATES & SURFACE PREPARATION

All	Surfaces must be clean, dry and free of contaminants.
Concrete or Concrete Masonry Units (CMU)	<p>Concrete must be cured a minimum of 7 days at 75°F (24°C) and 50% relative humidity or equivalent. Prepare surfaces in accordance with SSPC-SP 13/ NACE 6. Required surface profile is CSP 3-5. Voids in concrete surfaces may require filling. Mortar joints should be cured a minimum of 15 days.</p>

MIXING & THINNING

Mixing	Power mix separately, then combine and power mix.
Thinning	No thinning needed.
Ratio	2:1
Pot Life	<p>20 minutes at 77°F (25°C)</p> <p>15 minutes at 92°F (33°C)</p> <p>Not recommended below 60°F (16°C)</p> <p>Pot life is shorter at higher temperatures. A larger volume of mixed material will have a shorter pot life than a smaller volume.</p>

INSTALLATION GUIDELINES

Brush	Apply neat using medium bristle brush.
Roller	Short-nap synthetic roller cover with phenolic core.
Squeegee	Spread neat with notched squeegee for broadcast flooring and pavement overlays.
Pin Rake	Use pin rake to gauge slurry thickness when mixed with suitable aggregate.
Trowel	Use trowel to spread when mixed with filler or aggregate for concrete surfacing/releveling or flooring mortar.

PACKAGING & ESTIMATING

ITEM #	PRODUCT	PACKAGING
M-HF1200A-275IBC-1	Part A Resin	2400 lbs (1089 kg) / 255 gal (964 L)
M-HF1200B-275IBC-1	Part B Hardener	2250 lbs (1021 kg) / 259 gal (978 L)

Theoretical Coverage	26 square feet per gallon at 60 mils WFT Allow for loss in mixing and application.
-----------------------------	---

Storage & Shelf Life	Maintain products in original packaging and sealed until ready for use. Estimated shelf life is 12 months when stored in a dry area at 70°F (21°C). Actual shelf life may vary with storage conditions.
---------------------------------	---

If there is any question with respect to the quality of the components, check reactivity prior to use. For assistance consult with ErgonArmor.

TYPICAL PHYSICAL PROPERTIES

PROPERTY	VALUE
Mixed Case	Part A Resin, Part B Hardener (filler or aggregate not included)
Mixed Density	9.2 lbs/gal
Mixed Viscosity	4500 typical
Work Time	10 minutes
Application Temperature	60°F – 95°F (16°C – 35°C)

HFS BINDER SPECIFICATION

PROPERTY	SPECIFICATION
Gel Time, 50 mL volume ASTM C2471	25 minutes
Compressive Strength at 3 hours ASTM D695	1200 psi
Compressive Strength at 24 hours	6500 psi
Tensile Strength ASTM D638	2000 – 5000 psi
Elongation at Break ASTM D638	32%
Hardness, Shore D ASTM D2240	78
Adhesion Strength ASTM D4541	>7000 psi
Permeability to Chloride Ion at 28 days AASHTO T277	<100
Water Absorption at 24 hours ASTM D570	<0.10
Thermal Compatibility ASTM C884	Pass

Rev 12/2021

TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see ergonarmor.com.