

## SELECTION & SPECIFICATION DATA

<b>Type</b>	High flow vinyl ester polymer concrete
<b>Description</b>	Acrocast XF Concrete is a 3-component high flow vinyl ester polymer concrete designed for casting applications at least 1.5 inches (40 mm) thick that are exposed to oxidizing acids or alkaline chemicals.
<b>Uses</b>	<ul style="list-style-type: none"> <li>• Line or restore floors, walls, trenches and sumps</li> <li>• Fill cavities of structural glazed tile</li> <li>• Foundations, footings, pads and pedestals</li> <li>• Beams, columns, curbs and piers</li> <li>• Precast structures, shapes and assemblies</li> <li>• Rapid repair to deteriorated acid brick floors</li> <li>• Aprons around Acroline™ anchored thermoplastic lined trenches and sumps</li> </ul>
<b>Features</b>	<ul style="list-style-type: none"> <li>• Resistant to strong oxidizers, bleach solutions, and alkalis</li> <li>• Excellent flow characteristics</li> <li>• Excellent vibration resistance</li> <li>• High physical strength</li> <li>• Good bond to concrete and metal surfaces</li> <li>• Rapid strength gain</li> </ul>
<b>Limitations</b>	<ul style="list-style-type: none"> <li>• Requires formwork.</li> <li>• When using as an overlay in large surface areas, pour in a checkerboard fashion to reduce curing shrinkage stresses.</li> <li>• Not for use beyond its chemical resistance or thermal capabilities. Consult ErgonArmor with specific questions.</li> </ul>

## INSTALLATION GUIDANCE

<b>Reference Specifications</b>	CE-360 Installation of ErgonArmor Resinous Polymer Concretes
<b>Installation Conditions</b>	Substrate must be clean, dry and neutral pH. Acrocast XF Concrete is formulated for ideal handling at 70°F (21°C). Materials and substrate should be acclimated to the air temperature prior to installation, and the air temperature should be between 50°F (10°C) and 90°F (32°C) during installation and cure.
<b>Ratio</b>	<p>1 gallon resin: 2-3 fl. oz. hardener by volume. 1 part catalyzed resin: 7.0 parts filler by weight.</p> <p>Filler loading may be adjusted slightly to suit flow preferences. Where higher flow is required, reduce filler loading by holding back up to 0.7 parts filler.</p>
<b>Mixing</b>	Pour measured quantity of resin into clean, dry mixing vessel. Slowly add measured quantity of hardener to resin and power mix thoroughly. Add filler and power mix until filler is thoroughly wetted.
<b>Work Life</b>	<p>30-45 minutes at 70°F (21°C).</p> <p>Work life estimates are based on use of 2 fl. oz. CHP Hardener per 1 gallon resin. Increased hardener dosage will reduce work life.</p> <p>Work life is shorter at higher temperatures. A larger volume of mixed material will have a shorter work life than a smaller volume.</p>
<b>Cleanup</b>	Xylene or MEK

## CURE TIME

<b>Temperature</b>	<b>Initial Set</b>	<b>Full Cure</b>
70°F (21°C)	2-3 hours	3 days

## SAFETY

<b>Safety</b>	Mixes and applications of this product present a number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data sheets before using.
<b>Ventilation</b>	Provide thorough air circulation during and after application until the material has cured when used in enclosed areas.

### PACKAGING, ESTIMATING & HANDLING

Product	Code	Packaging
Acrocast Resin, Gray	19510	43 lb (5 gal) pail
	19511	446 lb (55 gal) drum
CHP Hardener	19552	11.2 fl. oz. (0.7 lb) bottle
	21922	1 gal (8.3 lb) can
Polymer Concrete XF Filler	23475	50 lb (22.6 kg) bag

A 2.6 cubic foot (344 lb) unit consists of 1 x 43 lb pail resin, 1 x 0.7 lb bottle of hardener, and 6 x 50-lb bags filler when mixed at 1.0 part mixed resin and hardener to 6.9 parts filler by weight.

A 27.1 cubic foot (3,604 lb) unit consists of 1 x 446 lb drum resin, 1 x 8.3 lb can hardener, and 63 x 50 lb bags filler when mixed at 1.0 part mixed resin and hardener to 6.9 parts filler by weight.

Mix can be made more fluid by holding back up to one half bag of filler for the 2.6 cubic foot unit or 7 bags for the 27.1 cubic foot unit. Yield will be reduced when filler is held back.

#### **Theoretical Coverage**

Allow 133 mixed lb/ft<sup>3</sup> (2,130 kg/m<sup>3</sup>) of volume. When casting as a 2-inch (50 mm) overlay, allow 22 mixed lb/ft<sup>2</sup> (108 kg/m<sup>2</sup>). For a 3-inch (76 mm) casting, allow 33 mixed lb/ft<sup>2</sup> (161 kg/m<sup>2</sup>). Normal wastage allowances should be added.

#### **Storage & Shelf Life**

Maintain products in original packaging and sealed until ready for use. Estimated shelf life is 4-6 months for resin, 12 months for hardener, and 36 months for filler when stored in a dry area at 70°F (21°C). Actual shelf life may vary with storage conditions.

If there is any question with respect to the quality of the components, check reactivity prior to use. For assistance consult with ErgonArmor.

### TYPICAL PHYSICAL PROPERTIES

Property	Typical Value
Color	Gray
Density, ASTM C138	133 lb/ft <sup>3</sup> (2,130 kg/m <sup>3</sup> )
Compressive strength, ASTM C579	>10,000 psi (69 MPa)
Tensile strength, ASTM C307	>1,800 psi (12.4 MPa)
Flexural strength, ASTM C580	>3,000 psi, (20.7 MPa)
Absorption, ASTM C413	0.4%
Linear shrinkage, ASTM C531	0.33%
Bond strength to concrete	Exceeds tensile strength of concrete
Minimum suggested application thickness	1.5 inches (40 mm). For castings under 1.5 inches (40 mm), use Acrocast XF Grout.
Slump using 6.9 filler: 1.0 mixed resin and hardener mix ratio	Approximately 7-8 inches (175-200 mm) with full filler loading.
Maximum service temperature	225°F (107°C)
Temperature limitations will vary with chemical service. Consult ErgonArmor Technical Service for guidance.	

Rev 09/2021

#### **TERMS AND CONDITIONS OF SALE**

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see [ergonarmor.com](http://ergonarmor.com).